

MP One 900

Gel - Junction Box Fillers



Products may differ in size, colour and appearance to those shown. If you require further information or customisation, please contact us directly.

Dielectric strength	25 kV/mm
Curing time at 23°C min	8
Volume	900 ml
Type	MP One 900
UK-Number	MP109
WISKA-Order no.	10111747
Packing unit	1
ETIM-Classification	EC001168

Remarks:

Colour: Blue

Shaking Time: 15 seconds

Description:

Silicone gel, no-expiry date, re-enterable, twist lid to release activation gel into the rest of the bottle, shake the bottle for 15 seconds then pour.

Additional Info:

Protection against rain, humidity, dust and intrusion.

20.05.2024

Your Contact:

WISKA UK Ltd.

Unit 7, Hurling Way · St. Columb Major Business Park · TR9 6SX, St. Columb Major, Cornwall · Great Britain

☎ +44-12-08816062 · 📠 +44-12-08816708

info@wiska.co.uk · www.wiska.co.uk